Codan 3111 Fuel Hose



Codan 3111 - SAE J30 R6

Flexible, black hose for leaded and unleaded petrol, to SAE 30 R6.

Good ozone resistance. Resistant to oil spray in engine compartments.

For fuel pipes in cars, lorries, lawn mowers, garden

cultivators, etc.

Acc. EN228:2008 and EN590:2010

Please contact Codan for further information.

Type nr. 3111

Application: Fuel / Diesel **Standard Length:** 50 metres

Working Temperature: -30°C to 90°C

Inside: NBR Colour: Black Reinforcement: PVA

Outside: CR Colour: Black

Standards: SAE J30 R6

Inside dia. (mm)	Outside dia. (mm)	Working Pressure BAR	Burst Pressure BAR	Bend Radius (mm)	Weight (g/m)	Product code
3,2	9,2	5	50	15	95	311103200
3,5	9,5	5	50	15	98	311103500
4,0	10,0	5	50	15	100	311104000
4,8	10,8	5	50	15	110	311104800
5,0	11,0	5	50	20	120	311105000
5,5	11,5	5	50	20	125	311105500
6,0	12,0	5	50	20	130	311106000
6,3	12,7	5	50	20	130	311106300
7,9	14,7	5	50	45	160	311107900
8,0	14,0	5	50	25	180	311108000
9,5	16,7	5	50	40	200	311109500
10,0	17,0	5	50	40	230	311110000
11,0	18,2	5	50	45	250	311111000
12,7	19,7	5	50	50	257	311112700
13,0	20,0	5	50	50	270	311113000
16,0	24,0	5	50	80	320	311116000

This hose specification sheet has been prepared with great care in order to provide you with all the information you need. Written advice must be obtained from Codan Rubber before using any hose with untested media or before using in applications not covered in the product data sheet. Codan Rubber recommends regular maintenance, care and inspection of hoses before use. Hoses should be replaced if any physical damage is seen, especially to the cover of the hose or in the area around the couplings. All products must be stored in accordance with ISO 2230:2002 (Storage

of vulcanised Rubber Products). The individual conditions of an application will affect the life time of each product. Therefore please ensure that resistance to chemicals and cleaning procedures in our written product information is compiled with. Codan Rubber's warranty is void in the event of misuse such as excessive bending, crushing, stretching, use with incorrect media or use in environments outside the hose specification.

Please contact Codan Rubber for individual product manufacturing tolerances.



Codan Rubber A/S Værkstedsvej 45-49, DK-4600 Køge, Denmark Tel. +45 56 64 64 64 Fax +45 56 64 65 48 Mail: info@codan.com www.codan.com